

# Fomblin® Y-LOX 120

## perfluoropolyether

Fomblin® Y-LOX 120 perfluoropolyether fluids have the following unique features:

- Outstanding chemical stability
- Thermal stability
- Lubrication properties

### General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Asia Pacific • Europe • Latin America • North America
Features	• Chemical Resistant • High Density • High Heat Resistance
Forms	• Liquid

Physical	Typical Value	Unit	Test method
Specific Gravity	1.890	g/cm <sup>3</sup>	
Kinematic Viscosity			
20°C	120	cSt	ASTM D445
40°C	42.0	cSt	ASTM D445
100°C	6.80	cSt	
Surface Tension (25°C)	21	dyne/cm	
Vapor Pressure			
20°C	2E-4	torr	
100°C	5E-2	torr	
Viscosity Index	120		ASTM D2270

Thermal	Typical Value	Unit	Test method
Pour Point	-46	°C	ASTM D97

Additional Information	Typical Value	Unit	Test method
Weight Loss on Heating <sup>1</sup> (120°C)	< 10	%	ASTM D2595

## Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> 22 hr

# Fomblin® Y-LOX 120

## perfluoropolyether

---



---

**[www.syensqo.com](http://www.syensqo.com)**

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2025 2023 Syensqo. All rights reserved.